



Technical Data

Product: Polypro® CG200

Product Description:	Water-blown flotation foam Meets flotation foam specifications as listed in 46CFR 160.010 (B) (3), MIL-P-21929
Recommended Uses:	Poured or molded flotation applications
Shipping Containers:	Refillable pressure cylinders Disposable 55 gallon drums Disposable 275 gallon tote tanks

Recommended Dispensing Equipment: Hand mixed only

Processing Conditions

Ratio A:B (by weight):	105 : 100
Chemical Temperature:	75-90 °F
Cream Time:	25 seconds
Gel Time:	140 seconds
Rise Time:	200 seconds
Free Rise Density:	2.00 pounds/ cubic foot

Chemical Properties

	“A” Component	“B” Component
Specific Gravity @ 75° F	1.23	1.10
Viscosity, cps @ 75° F	200	1200

SAFETY WARNING: Polyurethane foam is combustible and may constitute a fire hazard if improperly used or stored. Read the Material Safety Data Sheet for further safety precautions.

DISCLAIMER: This information is believed to be true and accurate, but all recommendations are made without warranty, since the conditions of use are beyond the control of Polyfoam Products, Inc. (PPI). PPI requests that customers inspect and test our product before use, and satisfy themselves as to contents and sustainability. PPI assumes no responsibility for the product relative to its performance or injury resulting from its use. Liability, if any, is limited to replacement of materials.